

Sharp Cut Filter (Yellow)

Y-52

Catalog Thickness t = 2.5 mm

Reflection Factor P_d = 0.913

Diagram-1

Transmittance (T) & Internal Transmittance (τ) units: (%)

λ _{nm}	200	210	220	230	240	250	260	270	280	290	300	310	320	330	340	350	360	370	380	390	400	410	420	430	440	
T																										
τ																										
λ _{nm}	450	460	470	480	490	500	510	520	530	540	550	560	570	580	590	600	610	620	630	640	650	660	670	680	690	
T							1.1	40.6	75.0	86.3	89.5	90.7	91.1													
τ							1.2	44.5	82.1	94.5	98.0	99.3	99.8													
λ _{nm}	700	710	720	730	740	750	800	850	900	950	1,000	1,100	1,200	1,300	1,400	1,500	1,600	1,700	1,800	1,900	2,000	2,100	2,200	2,300	2,400	
T																										
τ																										

Refractive Indices

Symbol	i	h	g	F'	F	e	d	D	C'	C	r	A'	t
λ _{nm}	365.0	404.7	435.8	480.0	486.1	546.1	587.6	589.3	643.8	656.3	706.5	768.2	1,014.0
n						1.544	1.541	1.541	1.539	1.538	1.537	1.535	1.531

Abbe-Number

$$V_d = \frac{n_d - 1}{n_F - n_C} =$$

Color Specifications

	x	y	Y	λ _d	P _e
A	.538	.458	80.7	584	98
C	.490	.503	72.6	577	98
D ₆₅	.486	.507	72.5	576	98


Properties

Chemical		Thermal				Mechanical		Other
D _w	D _A	T _g	T _s	α _{-30/70}	α _{100/300}	H _K	F _A	S
2	1	560	620	96	108	540	130	2.68

Tolerances of Transmittance (T)

Transition Wavelength	Transition Interval	Average High Transmittance
λT(nm)	Δλ(nm)	T _H (%)
520 ± 5	< 25	> 85

Transmittance (T)



All data are mean values of various melts.

HOYA 8304E