

Material Safety Data Sheet (glass)

Product and company identification

Product name (brand name) R72

Name of company HOYA CANDEO OPTRONICS Corporation
 Address 3-5-24, Hikawa-cho, Toda-shi, Saitama, 335-0027 JAPAN
 Division in charge Quality & Environmental management
 Tel. +81- 48 - 447 - 6052
 FAX +81- 48 - 447 - 6053
 Issue date 23-Jun-16
 Update -

Composition, information on ingredients

Classification between single and
mixture products

Mixture

Chemical ingredient and content

Chemical name	Chemical formula	Industrial Safety and Health Law		PRTR (Pollutant Release and Transfer Register)						
		Hazardous material name to be notified	Content (Weight %)	Specified chemical substance name	Content (Weight %) Note 1,	Attached Table No.	No.	Class I designated substance	Specified Class I designated chemical substance	Class II designated substance
Silica	SiO ₂	Silica	40 to 50	-	-	-	-	-	-	-
Boron oxide	B ₂ O ₃	Boron trioxide	0 to 10	Boron and its compound	3.9	1	405	○	-	-
Zinc oxide	ZnO	Zinc oxide	20 to 30	Zinc water-soluble compound	22.5	1	1	○	-	-
Selenium	Se	Selenium and its compound	0 to 10	Selenium and its compound	0.80	1	242	○	-	-
Cadmium sulfide	CdS	Cadmium and its compound	0 to 10	Cadmium and its compound	2.57	1	75	○	○	-
Tellurium	Te	Tellurium and its compound	0 to 10	-	-	-	-	-	-	-

Note 1. Conforming to PRTR (Pollutant Release and Transfer Register), mass % of each ingredient is written.

Hazards identification

No health effects are expected from optical glass as it is physically and chemically stable.

Hazardous property: If the grinding and polishing liquids are swallowed or the dust generated is inhaled during dry cutting, it may be hazardous to chronic and accumulative health conditions, such as oncogenesis.

Environmental impact: Note the drainage concentration of grinding and polishing liquid. It may be hazardous to the ecosystem.

First aid measures

Eye contact : Rinse with clean water immediately when the eyes are affected by the grinding/polishing liquid. Refer to medical attention if required.
 Be careful not to hurt the eyes and refer for medical attention when the eyes are affected during dry cutting.

Mouth contact : Rinse the mouth when the mouth is affected by any of the grinding/polishing liquid and dust.
 If swallowed, drink large amounts of water and spit it out and refer for medical attention if required.

Fire-fighting measures

Optical glass is noncombustible and any extinguishing equipment can be used.

When glass is exposed to high temperatures due to a fire, fluoride gas may be generated. Therefore, move the glass concerned to a safe position promptly in case of a fire. When the fluoride gas is generated, do not stand in the direction of dust spill and wear a dust mask so as not to inhale the fluoride gas. Refer to medical attention when inhaling the gas.

Accidental release measures

Grinding and polishing : Stop spills with sandbags or the like, to prevent it from spreading into soil and flowing into liquid spills drainage systems.
 Dust spill : Prevent it from spreading into soil and flowing into drainage systems. Collect the dust spilled in an empty container. Do not stand in the direction of dust spill and wear a dust mask.

Handling and storage

Optical glass is physically and chemically stable so that no special cares are required when handling and storing.

When grinding, polishing and dry cutting

* Care should be taken not to scatter the grinding/polishing liquid, grinding/polishing waste and dust from dry cutting.

* After finishing the work, gargle and wash hands.

Exposure control and personal protection

Optical glass is physically and chemically stable, however, exposure may occur when mist and dust scatter during wet and dry cuttings, respectively.

Wet cutting: Use a protective cover for a processing machine to prevent the scattering of mist.

Dry cutting: Install a local exhaust system to prevent the scattering of dust. Wear a dust mask for the protective equipment.

Standard control concentration of chemical substance

Chemical substance name	Dust		
Standard control	E=2.9mg/m ³		

Physical and chemical properties

Physical condition : Solid
 Color : Black
 Odor : Odorless
 PH : Not applicable
 Physical condition changing temperature (yield point) : 575 °C
 Specific gravity : 2.86
 Solubility : Hardly soluble

Stability and reactivity

Stability : This product is stable.
 Reactivity : Usually no reactivity
 Decomposition : Usually none

Toxicological information

Optical glass is physically and chemically stable and has neither acute toxicity nor a local effect.

Grinding and polishing liquid, grinding/polish waste and dust have the following properties.

Acute toxicity: Not known

Carcinogenicity: Not known

Chronic Accumulative chronic toxicity is affected by inhalation and skin contact.

Ecological information

Optical glass is physically and chemically stable and has no influence on ecology.

When the grinding/polish drainage concentration exceeds the reference value of Water Pollution Control Law as shown below, the chronic toxicity of environmental accumulation is present.

Control subject substance			
Drainage standard or occupational exposure limits			

Disposal consideration

Conform to Wastes Disposal and Public Cleaning Law and contact an authorized disposal trader.

Transport information

No applicable information was found

Regulation information

Industrial Safety and Health Law, its enforcement ordinance and regulations,
Pneumoconiosis Law and its enforcement regulations,
Ordinance on Prevention of Hazards Due to Dust,
Ordinance on Prevention of Lead Poisoning,
Ordinance on Prevention of Hazards due to Specified Chemical Substance,
Working Environment Measurement Law, its enforcement ordinance, enforcement regulations, standard and work environment
Prefecture ministerial ordinance and notification stipulating Water Pollution Control Law, its enforcement ordinance, enforcement
PRTR (Pollutant Release and Transfer Register)
Wastes Disposal and Public Cleaning Law, its enforcement ordinance and enforcement regulations,

- Confirm the ordinance for the scale of office or installed capacity if applicable or not.
- Confirm regulations peculiar to a region separately.

Other information

Consult us separately when remelting the glass for recycling.
