

Internal Transmittance (τ)

λ nm	200	210	220	230	240	250	260	270	280	290	300	310	320	330	340	350	360	370	380	390
τ	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05
λ nm	400	410	420	430	440	450	460	470	480	490	500	510	520	530	540	550	560	570	580	590
τ	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05
λ nm	600	610	620	630	640	650	660	670	680	690	700	710	720	730	740	750	760	770	780	790
τ	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	0.013	0.263	0.663	0.863	0.931	0.955	0.964	0.968	0.970	0.971	0.972	0.973
λ nm	800	810	820	830	840	850	860	870	880	890	900	910	920	930	940	950	960	970	980	990
τ	0.974	0.973	0.973	0.974	0.974	0.975	0.975	0.976	0.976	0.977	0.978	0.979	0.980	0.980	0.983	0.983	0.983	0.985	0.985	0.986
λ nm	1000	1010	1020	1030	1040	1050	1060	1070	1080	1090	1100	1120	1140	1160	1180	1200				
τ	0.986	0.986	0.985	0.986	0.987	0.987	0.987	0.988	0.988	0.989	0.989	0.990	0.991	0.991	0.991					

Refractive Index/Absorption coefficient/Reflection coefficient

λ nm	400	500	600	700	800	900	1000
n	1.562	1.552	1.547	1.543	1.541	1.539	1.538
P	0.908	0.911	0.912	0.913	0.913	0.914	0.914

Classes of Bubbles and Inclusions

Bubble Class
3

Color Specification


	x	y	Y	λ_d	P_s
A	-	-	-	-	-
C	-	-	-	-	-
D65	-	-	-	-	-

Properties

Chemical		Thermal				Mechanical		Others
D_w	D_A	Tg	Ts	$\alpha_{-30/70}$	$\alpha_{100/300}$	H_K	F_A	d
1	3	525	575	98	115	470	160	2.86

Tolerance of Transmittance (τ)

$\lambda\tau_{0.5}$ (nm)	ΔL (nm)	ΔH (nm)
695±5	>610	>780



Internal Transmittance (τ)

λ nm	200	210	220	230	240	250	260	270	280	290	300	310	320	330	340	350	360	370	380	390
τ	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05
λ nm	400	410	420	430	440	450	460	470	480	490	500	510	520	530	540	550	560	570	580	590
τ	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05
λ nm	600	610	620	630	640	650	660	670	680	690	700	710	720	730	740	750	760	770	780	790
τ	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05	0.013	0.263	0.663	0.863	0.931	0.955	0.964	0.968	0.970	0.971	0.972	0.973
λ nm	800	810	820	830	840	850	860	870	880	890	900	910	920	930	940	950	960	970	980	990
τ	0.974	0.973	0.973	0.974	0.974	0.975	0.975	0.976	0.976	0.977	0.978	0.979	0.980	0.980	0.983	0.983	0.983	0.985	0.985	0.986
λ nm	1000	1010	1020	1030	1040	1050	1060	1070	1080	1090	1100	1110	1120	1130	1140	1150	1160	1170	1180	1190
τ	0.986	0.986	0.985	0.986	0.987	0.987	0.987	0.988	0.988	0.989	0.989	0.990	0.990	0.990	0.991	0.990	0.991	0.991	0.991	0.991
λ nm	1200	1210	1220	1230	1240	1250	1260	1270	1280	1290	1300	1310	1320	1330	1340	1350	1360	1370	1380	1390
τ	0.991	0.991	0.991	0.991	0.992	0.992	0.993	0.993	0.993	0.993	0.993	0.994	0.994	0.994	0.994	0.994	0.994	0.994	0.994	0.994
λ nm	1400	1410	1420	1430	1440	1450	1460	1470	1480	1490	1500	1510	1520	1530	1540	1550	1560	1570	1580	1590
τ	0.993	0.992	0.992	0.993	0.993	0.994	0.994	0.994	0.995	0.995	0.995	0.995	0.995	0.995	0.995	0.995	0.995	0.995	0.995	0.995
λ nm	1600	1610	1620	1630	1640	1650	1660	1670	1680	1690	1700	1710	1720	1730	1740	1750	1760	1770	1780	1790
τ	0.995	0.995	0.994	0.994	0.994	0.994	0.994	0.994	0.993	0.993	0.992	0.992	0.992	0.992	0.991	0.991	0.991	0.990	0.990	0.990
λ nm	1800	1810	1820	1830	1840	1850	1860	1870	1880	1890	1900	1910	1920	1930	1940	1950	1960	1970	1980	1990
τ	0.989	0.989	0.988	0.988	0.987	0.988	0.987	0.987	0.988	0.988	0.987	0.987	0.987	0.987	0.986	0.986	0.986	0.986	0.986	0.986
λ nm	2000	2050	2100	2150	2200	2250	2300	2350	2400	2450	2500	2550	2600	2650	2700	2750	2800	2850	2900	2950
τ	0.985	0.984	0.980	0.974	0.965	0.958	0.958	0.956	0.948	0.942	0.937	0.932	0.922	0.910	0.882	0.548	0.260	0.209	0.182	0.160
λ nm	3000	3050	3100	3150	3200	3250	3300	3350	3400	3450	3500	3550	3600	3650	3700	3750	3800	3850	3900	3950
τ	0.143	0.129	0.115	0.103	0.093	0.085	0.078	0.072	0.065	0.058	0.052	0.048	0.048	0.051	0.052	0.050	0.051	0.065	0.080	0.087
λ nm	4000	4050	4100	4150	4200	4250	4300	4350	4400	4450	4500	4550	4600	4650	4700	4750	4800	4850	4900	4950
τ	0.080	0.069	0.064	0.063	0.062	0.058	0.051	0.041	0.030	0.019	0.010	0.004	0.002	0.001	0.001	<1E-05	<1E-05	<1E-05	<1E-05	<1E-05
λ nm	5000																			
τ	<1E-05																			

